Slip Check to AS 4586-2013

ADORE SMOOTH GRIP

Report Number: R33318a
Report Date: 7 March 2025
Total Number of Pages 2

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Limited

Issued by	Prepared for	Approved by
Safe Environments Pty Limited 6/7 Inglewood Place Norwest NSW 2153	Stoneworld Method 1/28 Oramzi Road Girraween NSW 2145	Ratan Venkatesan Authorised Signatory

SlipCheck
CREATING SAFE ENVIRONMENTS
www.FloorSlipTest.com.au

6/7 Inglewood Place
Norwest NSW 2153
Phone02 9621 3706
info@SafeEnvironments.com.au

7 March 2025

Test Report No. R33318a

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by:	Stoneworld Method
Client Address:	1/28 Oramzi Road Girraween NSW 2145
Product Manufacturer:	Supplied by Stoneworld Method
Product Description:	ADORE SMOOTH GRIP
Test conducted according to:	AS 4586:2013 Appendix A
Sampling Procedures:	Performed by client and tested as received.
Location:	6/7 Inglewood Place, Norwest NSW 2153
Conducted by:	Nathan Vanderburg

Date:	07 March 2025	Temperature:	26°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	N/A		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	43	53	40	41	48

Reported SRV of Sample:	**45**
Class:	**P4**

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8 %, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd