GRIPTEK ANTI-SLIP SOLUTIONS PTY LTD
26a Production Avenue
Kogarah NSW 2217
AUSTRALIA
ABN: 13 622 802 797
T. 1300 01 GRIP
E. info@griptek.com.au

Test Report No: **170926B**

Slip Resistance Measurement of New Pedestrian Surfaces: AS4586:2013 Appendix A

Client:	Stoneworld - 1/28 Oramzi Road, Girraween NSW 2145		
Test Date:	17/09/2026	**Temperature:**	21 Deg. C
Test Conducted to:	AS 4586:2013 Appendix A	**Conducted by:**	Sean C Murphy B.A. (Syd. U), Dip. Ed
Test Method:	Wet Pendulum Testing	**Test Device:**	Munro - Serial No. 2015 Calibration Exp. 13/1/2027
Surface:	Renderstone	**Rubber Slider Used:**	Slider 96 (4 S Rubber) Cert. No. 96/464/26, BN:69
Slider Preparation:	Abrasive paper, Grade P400 followed by pink lapping paper wet		
Test Location:	1/28 Oramzi Road, Girraween NSW 2145		
Surface Preparation:	Cleaned with Water & Hand Scrubbing		
Surface Application:	N/A		

Tested Area:

Specimen Number	Location	Condition	Gradient %	Direction of Test	Mean BPN Last 3 swings
1	Loose Sample	As Found	<2.0	N/A	44
2	Loose Sample	As Found	<2.0	N/A	44
3	Loose Sample	As Found	<2.0	N/A	45
4	Loose Sample	As Found	<2.0	N/A	44
5	Loose Sample	As Found	<2.0	N/A	43

Mean BPN Slip Resistance Value - SRV **44**

Classification **P3**

Interpretation of the Wet Pendulum Results	
Classification of pedestrian surface materials according to the AS 4586	Mean BPN
P5	>54
P4	45-54
P3	35-44
P2	25-34
P1	12-24
P0	<12

The AS 4586 standard provides a guide & recommendation for use, we recommend that this report be read in conjuction with AS 4586 & Handbook HB198: 2014. Refer to Table 3B of HB 198 for requirements of sloped surfaces & ramps. The results in this test do not account for any future wear, contamination or maintenance of this surface. GripTek Anti-Slip Solutions Pty Ltd or our agents, licencees or employees accept no responsibility for any actions whatsoever which may arise as a result of this test report, all information within this report is copyright & is protected by copyright law.

Approved Signatory: Darryl Clisdell

D Clisdell